

Ricoh Electronics, Inc.

2320 Red Hill Ave., Santa Ana, CA 92705
1125 Hurricane Shoals Rd., Lawrenceville, GA 30043
Customer Service 1 (800) 843-7058
Toll-Free Fax 1 (888) 843-7059
e-mail: orders@rei.ricoh.com
http://www.rei.ricoh.com



THERMAL LABEL PAPER PRODUCT INFORMATION

130NIR-2

FACESTOCK

ITEM	SPECIFICATION	TEST METHOD
Basis Weight	47.3 # ± 4.3 (24 x 36 x 500 Sheets)	TAPPI T-410
	77 ± 7 g/m ²	
Caliper	3.1 Mils (79 ± 9µm)	TAPPI T-411
Image Color	Black	VISUAL CHECK
Image Density (ODU)	1.32 Minimum	Macbeth Densitometer
Background Density (ODU)	0.08 Maximum	Macbeth Densitometer
Tear Strength	MD 30 gf Minimum	TAPPI T-414
	CD 35 gf Minimum	
Tensile Strength	MD 5.0 kgf/15mm Minimum	TAPPI T-494
	CD 2.5 kgf/15mm Minimum	

PRESERVATION PROPERTIES

ITEM	SPECIFICATION	TEST METHOD
Plasticizer Resistance (Face)	Image 1.15 Minimum	40° C, Dry, 15 Hours
	Background 0.20 Maximum	
Water Resistance	Image 0.80 Minimum	Water Immersion, 15 Hours
	Background 0.20 Maximum	
Oil Resistance	Image 1.15 Minimum	40° C, Dry, 15 Hours
	Background 0.20 Maximum	
Moisture Resistance	Image 1.15 Minimum	40° C, 90% RH, 24 Hours
	Background 0.20 Maximum	
Heat Resistance	Image 1.15 Minimum	80° C, Dry, 24 Hours
	Background 0.20 Maximum	

*Remarks: Image and Background measured by Macbeth (ODU)

Scannable up to 660 nm

Specification may change without notice

130NIR-2 LAMINATED PRODUCT

GRADE	UNIT	G12	G24
Application Temperature	°F	-40 to 122	-40 to 122
	°C	-40 to 50	-40 to 50
Service Temperature	°F	-65 to 131	-65 to 131
	°C	-54 to 55	-54 to 55
Basis Weight (24 x 36 x 500)	LBS	97 ± 10	97 ± 10
	g/m ²	158 ± 17	158 ± 17
Caliper	µm	152 ± 17	152 ± 17

*Custom: Please contact the Sales/Marketing department for application specific adhesives.



Liner: 42# Super Calendered White Kraft

Caliper: 2.5 Mils ± 10% (64 ± 7µm)

Opacity: 65% Maximum (Photovolt)

STORAGE CONDITION

Below 95°F (35°C) and less than 85% RH in a warehouse avoiding direct sunlight.



Comments: Sensitivity curves are for general reference only.