

Specifications may change without notice Last update:

## 130PLL-RRE

## **Direct Thermal Linerless Label**

## SHEET

This product specification sheet provides the detail to aid you in identifying the most appropriate product type to meet your company's specific requirements. Please direct questions to: Ricoh Customer Service 1-800-843-7058


### DESCRIPTION

Ricoh's 130PLL-RRE Linerless direct thermal top coated label stock is ideal for high-speed printing providing superior barcode reliability. A silicone linerless product generates less waste and provide more labels per roll.

### **KEY FEATURES**

Silicone Linerless label that provides an environmentally friendly solution; Medium Sensitivity, Excellent Barcode Scannability, Removable Adhesive







Postal & Shipping Labels



**Quick Service Restaurant Labels** 

### **PROPERTIES**

COATED PRODU	CTPROPERTIES	UNIT	SPECIFICATION	TEST METHOD
Basis Weight	g/m2		93 ± 10	TAPPIT-410
Caliper	mil		3.5 ± 0.4	TAPPIT-411
	μm		88 ± 10	
Image Color			Black	Visual Check
Image Density	(ODU)	Minimum	1.00	X-Rite Densitometer

### PRESERVATION PROPERTIES

	ITEM	SPECIFICATION		TEST METHOD
Oil Resistance		Image	0.70 Minimum	20°C, Dry, 15 Hours
		Background	0.20 Maximum	X-Rite (ODU)
Moisture Resistance		Image	0.70 Minimum	40°C, 90% RH, 15 Hours
		Background	0.20 Maximum	X-Rite (ODU)
Heat Resistance		Image	0.70 Minimum	90°C, Dry, 1 Hour
		Background	0.20 Maximum	X-Rite (ODU)
Light Lesistance		Image	0.70 Minimum	Fluorescent Lamp 5klx, 100 Hours
		Background	0.20 Maximum	X-Rite (ODU)

### ADHESIVE PROPERTIES

ITEM	UNIT	SPECIFICATION	TEST METHOD
Shear Resistance	mm	2.00 Maximum	1kg, 30min, 25mm×25mm, 22°C 55%
Release Value	mN/40mm	300 Maximum	300mm/min, 22°C 55%
Peel Adhesion	N/25mm	1.00 Minimum	SUS, 300mm/min, 22°C 55%




# 130PLL-RE

## **Direct Thermal Linerless Label**


### SENSITIVITY RESULTS

**Optical Density** 

## **Dynamic Sensitivity**



## **Static Sensitivity**



Temperature (°C)

Sensitivity curves are for reference only.

Storage Conditions: Below 95°F (35°C) and less than 85% R.H. in a warehouse, avoiding direct sunlight.

Tests performed on Markpoint MP104.

#### 130PLL-RRE - ADHESIVE PROPERTY

GRADE	UNIT	Adhesive	
Application	°F	41 to 95	
Temperature	٥C	5 to 35	
Service	°F	41 to 95	
Temperature	٥С	5 to 35	

## CERTIFICATES / REGULATIONS / DIRECTIVES

**BPA Free** RoHS ISO9001 **REACH** WEEE ISO14001

RICOH ELECTRONICS, INC. DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THE CUSTOMER'S PURCHASE OF OUR PRODUCTS. IT IS CUSTOMER'S SOLE AND EXCLUSIVE RESPONSIBILITY TO TEST AND ENSURE SUITABILITY OF OUR PRODUCTS FOR ITS CUSTOMERS' OR END-USER'S APPLICATION.

## CONTACT

Copyright 2016 Ricoh Electronics, Inc. 1125 Hurricane Shoals Rd.

Lawrenceville, GA 30043

All Rights Reserved

**Company Info** ISO14001 / ISO9001 Certified **Customer Service Department** Toll-Free 1-800-843-7058 Toll-Free Fax 1-888-873-7059

Worldwide Fax +1-714-259-4349 Email: orders@rei.ricoh.com