



SPECIFICATION SHEET

This product specification sheet provides the detail to aid you in identifying the most appropriate product type to meet your company's specific requirements. Please direct questions to: **Ricoh Customer Service 1-800-843-7058**

DESCRIPTION

130NIR-3 is a medium sensitivity top coated thermal label stock, heat resistant, and able to scan up to 670nm.

KEY FEATURES

Near infrared readability; able to scan up to 670nm
 Moderate image preservation properties; Medium sensitivity and good image resolution.

— APPLICATION AREAS —



Shipping Labels



Distribution Labels

FACESTOCK / PRESERVATION PROPERTIES

FACESTOCK PROPERTIES

ITEM		UNIT	SPECIFICATION	TEST METHOD
Basis Weight		lbs (24x36x500 sheets)	43 ± 5	TAPPI T-410
		g/m ²	70 ± 7	
Caliper		mil	3.0 ± 0.3	TAPPI T-411
		µm	76 ± 7	
Image Color			Black	Visual Check
Image Density	(ODU)	Minimum	1.00	X-Rite Densitometer
Tear Strength	MD	gf Minimum	25	TAPPI T-414
	CD	gf Minimum	30	
Tensile Strength	MD	kgf/15 mm Minimum	5.4	TAPPI T-494
	CD	kgf/15 mm Minimum	2.7	
Stiffness	MD	g-cm Minimum	3.0	TAPPI T-489
	CD	g-cm Minimum	2.0	
Initial Activation Temperature	(O.D. = 0.2)	°F / °C	212 / 100	
Effective Activation Temperature	(O.D. = 0.8)	°F / °C	257 / 125	


PRESERVATION PROPERTIES

ITEM	SPECIFICATION	TEST METHOD
Oil Resistance	Image	0.80 Minimum
	Background	0.20 Maximum
Moisture Resistance	Image	40° C, 90% RH, 24 Hours
	Background	0.20 Maximum
Heat Resistance	Image	80° C, Dry, 1 Hour
	Background	0.20 Maximum




SENSITIVITY RESULTS

Dynamic Sensitivity



Static Sensitivity



Sensitivity curves are for reference only.

Storage Conditions: Below 95°F (35° C) and less than 85% R.H. in a warehouse, avoiding direct sunlight.

Tests performed on Markpoint MP104.

130NIR-3 – LAMINATED PRODUCT

GRADE	UNIT	G25
Application	°F	-40 to 122
Temperature	°C	-40 to 50
Service	°F	-65 to 131
Temperature	°C	-54 to 55
Basis Weight	lbs	98 ± 12
(24 x 36 x 500)	g/m ²	160 ± 19
Caliper	µm	152 ± 18
	mil	6.0 ± 0.7

Liner: 40 lbs

Caliper: 2.5 mils ± 10% (64 ± 8 µm)

Opacity: 65% Maximum (Photovolt)

Adhesive Attributes:

G25 – Wide Temperature and Permanent

CERTIFICATES / REGULATIONS / DIRECTIVES

BPA Free

ISO9001

ISO14001

Indirect Food Contact

RICOH ELECTRONICS, INC. DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THE CUSTOMER'S PURCHASE OF OUR PRODUCTS. IT IS CUSTOMER'S SOLE AND EXCLUSIVE RESPONSIBILITY TO TEST AND ENSURE SUITABILITY OF OUR PRODUCTS FOR ITS CUSTOMERS' OR END-USER'S APPLICATION.

CONTACT INFORMATION

Copyright 2016 Ricoh Electronics, Inc.
 1125 Hurricane Shoals Rd.
 Lawrenceville, GA 30043
 All Rights Reserved

Company Info
 ISO14001 / ISO9001 Certified

Customer Service Department
 Toll-Free 1-800-843-7058
 Toll-Free Fax 1-888-873-7059
 Worldwide Fax +1-770-613-6478
 Email: orders@rei.ricoh.com