RICOH imagine. change. Jul 2023 PS-2356 (Rev. 5)

Specifications may change without notice Last update:

130PLL-RRE

Direct Thermal Linerless Label

ON SHEET C

This product specification sheet provides the detail to aid you in identifying the most appropriate product type to meet your company's specific requirements. Please direct questions to: Ricoh Customer Service 1-800-843-7058

DESCRIPTION

KEY FEATURES

Ricoh's 130PLL-RRE Linerless direct thermal top coated label stock is ideal for high-speed printing providing superior barcode reliability. A silicone linerless product generates less waste and provide more labels per roll.

Silicone Linerless label that provides an environmentally friendly solution; Medium Sensitivity, Excellent Barcode Scannability, Removable Adhesive

Ν Δ R F Т Ο



Weigh Scale Labels



Postal & Shipping Labels

PROPERTIES

COATED PRODUCT PROPERTIES UNIT SPECIFICATION TEST METHOD					
Basis Weight	g/m2		93 ± 10	TAPPI T-410	
Caliper	mil		3.5 ± 0.4	TAPPI T-411	
	μm		88 ± 10	TAPPI 1-411	
Image Color			Black	Visual Check	
Image Density	(ODU)	Minimum	1.00	X-Rite Densitometer	

PRESERVATION PROPERTIES

ІТ	EM	SPECIFICATION		TEST METHOD
Oil Resistance		Image	0.70 Minimum	20°C, Dry, 15 Hours
On Resistance		Background	0.20 Maximum	X-Rite (ODU)
Moisture Resistance		Image	0.70 Minimum	40°C, 90% RH, 15 Hours
		Background	0.20 Maximum	X-Rite (ODU)
Heat Resistance		Image	0.70 Minimum	90°C, Dry, 1 Hour
		Background	0.20 Maximum	X-Rite (ODU)
Light Logistopoo		Image	0.70 Minimum	Fluorescent Lamp 5klx, 100 Hours
Light Lesistance		Background	0.20 Maximum	X-Rite (ODU)

ADHESIVE PROPERTIES

ITEM	UNIT	SPECIFICATION	TEST METHOD
Shear Resistance	mm	2.00 Maximum	1kg, 30min, 25mm×25mm, 22°C 55%
Release Value	mN/40mm	300 Maximum	300mm/min, 22°C 55%
Peel Adhesion	N/25mm	1.00 Minimum	SUS, 300mm/min, 22°C 55%

Ricoh Electronics, Inc. • 1125 Hurricane Shoals Road • Lawrenceville, GA 30043 • www.RicohThermalProducts.com Customer Service: 1.800.843.7058 • Toll Free FAX: 1.888.843.7059 • email: orders@rei.ricoh.com



Specifications may change without notice Last update: Jul 2023


130PLL-RE

Direct Thermal Linerless Label

SENSITIVITY RESULTS

Dynamic Sensitivity





Sensitivity curves are for reference only.

Storage Conditions: Below 95°F (35° C) and less than 85% R.H. in a warehouse, avoiding direct sunlight. Tests performed on Markpoint MP104.

	130PLL-RRE	- ADHESIVE	PROPERTY
GRADE	UNIT	Hotmelt Removable Adhesive	
Application	°F	41 to 95	
Temperature	°C	5 to 35	
Service	°F	41 to 95	
Temperature	°C	5 to 35	

CERTIFICATES / REGULATIONS / DIRECTIVES

BPA Free

ISO9001

ISO14001

Indirect Food Contact

RICOH ELECTRONICS, INC. DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THE CUSTOMER'S PURCHASE OF OUR PRODUCTS. IT IS CUSTOMER'S SOLE AND EXCLUSIVE RESPONSIBILITY TO TEST AND ENSURE SUITABILITY OF OUR PRODUCTS FOR ITS CUSTOMERS' OR END-USER'S APPLICATION.

CONTACT ΙΝΕΟΚΜΑΤΙΟΝ

Copyright 2016 Ricoh Electronics, Inc. 1125 Hurricane Shoals Rd. Lawrenceville, GA 30043 All Rights Reserved

Company Info ISO14001 / ISO9001 Certified

Customer Service Department Toll-Free 1-800-843-7058 Toll-Free Fax 1-888-873-7059 Worldwide Fax +1-714-259-4349 Email: orders@rei.ricoh.com