



## SPECIFICATION SHEET

This product specification sheet provides the detail to aid you in identifying the most appropriate product type to meet your company's specific requirements.  
Please direct questions to: **Ricoh Customer Service 1-800-843-7058**

### DESCRIPTION

N140PF G12's direct thermal top coated label stock is durable, has high sensitivity, strong resistance to plasticizers, and prints at high speeds

### Key Features

Completely Phenol Free, Standard top-coated, Medium-high image resolution, High sensitivity, Strong image preservation against most environments



## — APPLICATION AREAS —



Weigh Scale Labels



Shipping Labels



Meat Processing



Distribution/Inventory



Product ID

## FACESTOCK / PRESERVATION PROPERTIES

### FACESTOCK PROPERTIES


ITEM		UNIT	SPECIFICATION	TEST METHOD
Basis Weight		lbs (24x36x500 sheets)	43.6 ± 4.3	TAPPI T-410
		g/m2	71 ± 7	
Caliper		mil	3.0 ± 0.3	TAPPI T-411
		µm	76 ± 7	
Image Color			Black	Visual Check
Image Density	(ODU)	Minimum	1.25	X-Rite Densitometer
Tear Strength	MD	gf Minimum	30.0	TAPPI T-414
	CD	gf Minimum	35.0	
Tensile Strength	MD	kgf/15 mm Minimum	5.4	TAPPI T-494
	CD	kgf/15 mm Minimum	2.7	
Stiffness	MD	g-cm Minimum	3.0	TAPPI T-489
	CD	g-cm Minimum	2.5	
Initial Activation Temperature	(O.D. = 0.2)	°F / °C	212 / 100	
Effective Activation Temperature	(O.D. = 0.8)	°F / °C	239 / 115	

### PRESERVATION PROPERTIES


ITEM		SPECIFICATION	TEST METHOD
Oil Resistance	Image	1.10 Minimum	40° C, Dry, 15 Hours X-Rite (ODU)
	Background	0.15 Maximum	
Moisture Resistance	Image	1.10 Minimum	40° C, 90% RH, 24 Hours X-Rite (ODU)
	Background	0.12 Maximum	
Heat Resistance	Image	1.10 Minimum	80° C, Dry, 1 Hour X-Rite (ODU)
	Background	0.30 Maximum	
Light Resistance	Image	1.10 Minimum	5,000 lx, 100 Hours X-Rite (ODU)
	Background	0.15 Maximum	

## SENSITIVITY RESULTS

### Dynamic Sensitivity



### Static Sensitivity



Sensitivity curves are for reference only.

Storage Conditions: Below 95°F (35° C) and less than 85% R.H. in a warehouse, avoiding direct sunlight.

Tests performed on Markpoint MP104.

## N140PF G12 – LAMINATED PRODUCT

GRADE	UNIT	G12 AT
Application	°F	-40 to 122
Temperature	°C	-40 to 50
Service	°F	-65 to 131
Temperature	°C	-54 to 55
Basis Weight	lbs	90 ±10
(24 x 36 x 500)	g/m <sup>2</sup>	147 ±17
Caliper	µm	141 ±17
	mil	5.6 ± 0.7

### Adhesive Attributes:

G12 – Wide Temperature and Permanent (AT)

Caliper: 2.1 mils ± 10% (55 ± 7 µm)

Opacity: 65% Maximum (Photovolt)

## CERTIFICATES / REGULATIONS / DIRECTIVES

Phenol Free

ISO9001

ISO14001

Indirect Food Contact

RICOH ELECTRONICS, INC. DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THE CUSTOMER'S PURCHASE OF OUR PRODUCTS. IT IS CUSTOMER'S SOLE AND EXCLUSIVE RESPONSIBILITY TO TEST AND ENSURE SUITABILITY OF OUR PRODUCTS FOR ITS CUSTOMERS' OR END-USER'S APPLICATION.

## CONTACT INFORMATION

**Copyright 2020 Ricoh Electronics, Inc.**

1125 Hurricane Shoals Rd.

Lawrenceville, GA 30043

All Rights Reserved

**Company Info**

ISO14001 / ISO9001 Certified

**Customer Service Department**

Toll-Free 1-800-843-7058

Toll-Free Fax 1-888-873-7059

Worldwide Fax +1-770-613-6478

Email: [orders@rei.ricoh.com](mailto:orders@rei.ricoh.com)