



SPECIFICATION SHEET

This product specification sheet provides the detail to aid you in identifying the most appropriate product type to meet your company's specific requirements.
Please direct questions to: Ricoh Customer Service 1-800-843-7058

DESCRIPTION

Ricoh's 140LES is a high sensitivity polypropylene direct thermal film stock with high image durability against most environments.

KEY FEATURES

High sensitivity, high image preservation properties; durable polypropylene base film that is tear and water resistant.

APPLICATION AREAS



FACESTOCK / PRESERVATION PROPERTIES

FACESTOCK PROPERTIES

ITEM		UNIT	SPECIFICATION	TEST METHOD
Basis Weight		lbs (24x36x500 sheets)	49.2 ± 4.9	TAPPI T-410
		g/m2	80 ± 8	
Caliper		mil	3.9 ± 0.4	TAPPI T-411
		µm	99 ± 10	
Image Color			Black	Visual Check
Image Density	(ODU)	Minimum	1.30	X-Rite Densitometer
Tensile Strength	MD	Kgf/15mm	15.0 Min.	TAPPI T-494
	CD	Kgf/15mm	25.0 Min.	
Stiffness	MD	gf-cm Minimum	7.84	TAPPI T-489
	CD	gf-cm Minimum	11.76	
Initial Activation Temperature	(O.D. = 0.2)	°F / °C	203 / 95	
Effective Activation Temperature	(O.D. = 0.8)	°F / °C	221 / 105	


PRESERVATION PROPERTIES

ITEM		SPECIFICATION	TEST METHOD
Oil Resistance	Image	1.20 Minimum	40° C, Dry, 15 Hours
	Background	0.15 Maximum	X-Rite (ODU)
Moisture Resistance	Image	1.20 Minimum	40° C, 90% RH, 24 Hours
	Background	0.15 Maximum	X-Rite (ODU)
Heat Resistance	Image	1.20 Minimum	70° C, Dry, 24 Hours
	Background	0.20 Maximum	X-Rite (ODU)
Water Resistance	Image	1.00 Minimum	Water Immersion, 15 Hours
	Background	0.12 Maximum	X-Rite (ODU)




SENSITIVITY RESULTS

Dynamic Sensitivity



Static Sensitivity



Sensitivity curves are for reference only.

Storage Conditions: Below 95°F (35° C) and less than 85% R.H. in a warehouse, avoiding direct sunlight.

Tests performed on Markpoint MP104.

140LES – LAMINATED PRODUCT

GRADE	UNIT	G8	G12	G22
Application	°F	10 to 120	-40 to 122	28 to 120
Temperature	°C	-12 to 49	-40 to 50	-2 to 50
Service	°F	-20 to 120	-65 to 131	-40 to 122
Temperature	°C	-29 to 49	-54 to 55	-40 to 50
Basis Weight	lbs	101 ± 11	105 ± 11	105 ± 11
(24 x 36 x 500)	g/m ²	164 ± 18	171 ± 18	170 ± 18
Caliper	µm	178 ± 21	179 ± 21	179 ± 21
	mil	7.0 ± 0.8	7.0 ± 0.8	7.0 ± 0.7

Liner: 42 lbs

Caliper: 2.5 mils ± 10% (64 ± 8 µm)

Opacity: 65% Maximum (Photovolt)

Adhesive Attributes:

G12 – Wide Temperature and Permanent

G8 – Tight Removable

G22 – Hot Melt for High Moisture Environments

CERTIFICATES / REGULATIONS / DIRECTIVES

BPA Free	BPS Free	ISO9001	ISO14001	Indirect Food Contact
No Added PFAS				

RICOH ELECTRONICS, INC. DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THE CUSTOMER'S PURCHASE OF OUR PRODUCTS. IT IS CUSTOMER'S SOLE AND EXCLUSIVE RESPONSIBILITY TO TEST AND ENSURE SUITABILITY OF OUR PRODUCTS FOR ITS CUSTOMERS' OR END-USER'S APPLICATION.

CONTACT INFORMATION

Copyright 2024 Ricoh Electronics, Inc.
1125 Hurricane Shoals Rd.
Lawrenceville, GA 30043
All Rights Reserved

Company Info
ISO14001 / ISO9001 Certified

Customer Service Department
Toll-Free 1-800-843-7058
Toll-Free Fax 1-888-873-7059
Worldwide Fax +1-770-613-6478
Email: orders@rei.ricoh.com