

Specifications may change without notice Last update: Sep 2024

# 130PLL-RN

### **Direct Thermal Linerless Label**

This product specification sheet provides the detail to aid you in identifying the most appropriate product type to meet your company's specific requirements. Please direct questions to: Ricoh Customer Service 1-800-843-7058

#### DESCRIPTION

Ricoh's 130PLL-RN Linerless direct thermal top coated label stock is ideal for high-speed printing providing superior barcode reliability. A silicone linerless product generates less waste and provide more labels per roll.

### **KEY FEATURES**

Silicone Linerless label that provides an environmentally friendly solution; Medium Sensitivity, Excellent Barcode Scannability

### R







Postal & Shipping Labels

### **PROPERTIES**

#### **COATED PRODUCT PROPERTIES**

	ITEM	UNIT	SPECIFICATION	TEST METHOD	
Basis Weight	g/m2		93 ± 10	TAPPI T-410	
Caliper	mil		3.5 ± 0.4	TAPPI T-411	
Calibei	μm		88 ± 10	TAPPI 1-411	
Image Color			Black	Visual Check	
Image Density	(ODU)	Minimum	1.00	X-Rite Densitometer	

#### PRESERVATION PROPERTIES

	ITEM	SPECIFICATION		TEST METHOD
Oil Resistance		Image	0.70 Minimum	20°C, Dry, 15 Hours
		Background	0.20 Maximum	X-Rite (ODU)
		Image	0.70 Minimum	40°C, 90% RH, 15 Hours
Moisture Resistance		Background	0.20 Maximum	X-Rite (ODU)
Hart Basistana		Image	0.70 Minimum	90°C, Dry, 1 Hour
Heat Resistance		Background	0.20 Maximum	X-Rite (ODU)
Light Logistaneo		Image	0.70 Minimum	Fluorescent Lamp 5klx, 100 Hours
Light Lesistance		Background	0.20 Maximum	X-Rite (ODU)

#### **ADHESIVE PROPERTIES**

ITI	EM UNIT	SPECIFICATION	TEST METHOD
Shear Resistance	m m	2.00 Maximum	1kg, 30min, 25mm×25mm,
Shear Resistance	mm		22°C 55%
Release Value	mN/40mm	300 Maximum	300mm/min, 22°C 55%
Peel Adhesion	N/25mm	12.7 Minimum	SUS, 300mm/min, 22°C 55%




# 130PLL-RN

### **Direct Thermal Linerless Label**


### SENSITIVITY RESULTS

**Optical Density** 

### **Dynamic Sensitivity**



### Static Sensitivity



Sensitivity curves are for reference only.

Storage Conditions: Below  $95^{\circ}F$  ( $35^{\circ}$  C) and less than 85% R.H. in a warehouse, avoiding direct sunlight.

Tests performed on Markpoint MP104.

### 130PLL-RN - ADHESIVE PROPERTY

GRADE	UNIT	Hotmelt Permanent Adhesive	
Application	٥F	41 to 95	
Temperature	°C	5 to 35	

## CERTIFICATES / REGULATIONS / DIRECTIVES

BPA Free No Added PFAS

ISO9001

ISO14001

**Indirect Food Contact** 

RICOH ELECTRONICS, INC. DISCLAIMS ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THE CUSTOMER'S PURCHASE OF OUR PRODUCTS. IT IS CUSTOMER'S SOLE AND EXCLUSIVE RESPONSIBILITY TO TEST AND ENSURE SUITABILITY OF OUR PRODUCTS FOR ITS CUSTOMERS' OR END-USER'S APPLICATION.

### CONTACT INFORMATION

**Copyright 2024 Ricoh Electronics, Inc.** 1125 Hurricane Shoals Rd.

Lawrenceville, GA 30043 All Rights Reserved Company Info ISO14001 / ISO9001 Certified Customer Service Department
Toll-Free 1-800-843-7058
Toll-Free Fax 1-888-873-7059
Worldwide Fax +1-714-259-4349

Email: orders@rei.ricoh.com