

140LES HR G5 PF DIRECT THERMAL

Specifications may change without notice.
Last Update: January 2026 PS-2533 (Rev. 1)



PRODUCT FEATURES

140LES HR G5 PF is a Phenol-free, high-sensitivity polypropylene direct thermal film stock with a 3.9 mil base film thickness, featuring a high-release liner and hot melt adhesive. Designed for applications requiring exceptional durability and high-quality imaging, its tear- and water-resistant base film ensures reliable performance in demanding environments.

APPLICATION AREAS

- Ski Lift Tickets





FACESTOCK PROPERTIES

Basis Weight	
lbs (24 x 36 x 500 sheets)	49.2 ± 4.9
g/sq m	80 ± 8
Caliper	
mil	3.9 ± 0.4
µm	99 ± 10
Image Density (ODU Minimum)	
	1.30
Tensile Strength (kgf/15 mm Minimum)	
MD	15.0
CD	25.0
Stiffness (gf-cm Minimum)	
MD	7.84
CD	11.76
Initial Activation Temperature	
(°F / °C)	
O.D. = 0.2	203°F / 95°C
Effective Activation Temperature	
(°F / °C)	
O.D. = 0.8	221°F / 105°C

CERTIFICATIONS

- Indirect Food Contact
- ISO9001
- ISO14001

REGULATORY

-  Phenol Free
-  BPS Free
-  BPA Free
-  No Added PFAS

PRESERVATION PROPERTIES

Oil Resistance

Image	1.10 Minimum
Background	0.15 Maximum
Test Method	40°C, Dry, 15 Hrs, X-Rite (ODU)

Moisture Resistance

Image	1.10 Minimum
Background	0.15 Maximum
Test Method	40°C, 90% RH, 24 Hrs, X-Rite (ODU)

Heat Resistance


Image	1.10 Minimum
Background	0.30 Maximum
Test Method	90°C, Dry, 1 Hr, X-Rite (ODU)

Light Resistance


Image	1.10 Minimum
Background	0.15 Maximum
Test Method	5000 lx, 100 Hrs, X-Rite (ODU)

140LES HR G5 PF DIRECT THERMAL SENSITIVITY RESULTS

DYNAMIC SENSITIVITY



STATIC SENSITIVITY



Sensitivity curves for reference only. Storage Conditions: Below 95°F (35°C) and less than 85% R.H. in a warehouse, avoiding direct sunlight. Dynamic sensitivity tests performed on Markpoint MP104.

LINER AND ADHESIVE PROPERTIES

Liner: 40 lbs (24 x 36 x 500)

G5 Adhesive: General Purpose Hot Melt

Caliper: 2.4 mils ± 10% (61 ± 6µm)

Opacity: 65% Maximum (Photovolt)

LAMINATED PRODUCT PROPERTIES

Application Temperature	G5
°F	35 to 120
°C	2 to 49
Service Temperature	
°F	-40 to 120
°C	-40 to 49
Basis Weight (24 x 36 x 500)	
lbs	105 ± 11
g/sq m	171 ± 18
Caliper	
mil	7.2 ± 0.8
µm	183 ± 21

CONTACT US

1125 Hurricane Shoals Road,
Lawrenceville, GA 30043

www.REI.Ricoh.com

Email: Orders@rei.ricoh.com

Customer Service:

(800) 843-7059

Toll-Free Fax: (888) 873-7059